

TECHNICAL DATA SHEET

50% HYDROCURE ZDEC DISPERSION (DRAFT)

50% Hydrocure ZDEC is a stable aqueous dispersion of Zinc Diethyl Dithiocarbamate and used as a fast, low-temperature Accelerator for both Synthetic & Natural Rubber Latices.

50% Hydrocure ZDEC is an easy to handle, mobile, water based dispersion that demonstrates excellent storage stability. Manufactured to a very fine particle size with a high surface area that may contribute to reduced loading and user added value.

50% Hydrocure ZDEC conforms to FDA 21CFR 177.2600 (Rubber Articles intended for Repeated Use).

PARAMETER	SPECIFICATION
Viscosity (dPs):	75 (+ / - 25)
pH:	8.00 - 11.0
Specific Gravity:	1.15 – 1.25
TSC (%):	>50
Particle Size Microns:	d75 < 3 μ

PACKAGING:

60 L Mausers, 125 & 200 L DRUMS

Note: The information in this document is based on current knowledge and experience. Many factors can affect processing and application of this product, information contained does not imply or guarantee suitability or final user result. It is highly recommended that users conduct their own tests/trials to determine suitability to their product and processes.

DVM Reviewed: 14.09.15